

# *mju:wax*<sup>®</sup> 2994

**Product description**                      **micronised wax compound**                      **EINECS: preparation**

---

*mju:wax*<sup>®</sup> 2994 is a micronised wax compound.

<b>Characteristic</b>	<b>Unit</b>	<b>Target value</b>
Appearance	-	white powder
Drop point	°C	138
Particle size (D <sub>50</sub> )	µm	5.5
Particle size (D <sub>90</sub> )	µm	11
Acid value	mg KOH/g	4
Density (23°C)	g/cm <sup>3</sup>	0.95

## **Major fields of application**

---

*mju:wax*<sup>®</sup> 2994 is a micronised wax additive to provide hydrophobic properties in paints, coatings and stains. *mju:wax*<sup>®</sup> 2994 improves immediate as well as long-lasting water repellency. Dosage levels are typically between 2 - 4% depending on usage for vertical and/or horizontal surfaces.

*mju:wax*<sup>®</sup> 2994 can be used together with silicas to improve weather resistance in combination with a uniform matting effect.

## **Packaging**

---

Paper-bags of 20 kg netto.

## **Storage**

---

The product has to be stored dry at room temperature.

Beware of sunlight and heat.

Stability at least 2 years from date of delivery.

## **Hazards**

---

This product does not require labelling in terms of preparation guideline. Further security relevant data see safety data sheet.

## **Ecology/toxicology properties**

---

The product is water insoluble. Further information see material safety data sheet.

## **Status under food legislation**

---

The product fulfills legislations of various countries. More details on request.

All information given here are based on our own research or the research of others and believed to be accurate and shall give the user guidance for the application. Nevertheless these data are no specification and due to the versatile possible formulations, applications, processings and further parameters at the formulator/user the usage of this product has to be tested carefully in the particular system/application by the formulator/user. All information mentioned here are not warranted properties. There is no responsibility of the seller if the material is used outside the recommended field of use; any liability, also for any patent infringement, cannot be derived from this.